



## **Refreshing Charge Procedure for Motive Power/Traction Cells**

1. Check the Acid-level . should be at least above the separator level.
2. Charge at 0.1C5 Amps. for 12 hours minimum or till Specific gravity and Voltage of Pilot cells remain constant over a period of 3 hours.
3. Top-up to the maximum level with 1.260 . 1.280 gravity acid and continue charging at 0.05C5 Amps. for at least two more hours.
4. Give rest till electrolyte temperature comes down to 35°C before putting into application or conducting discharge test.