











































































## General Technical Particulars

Type of Cell	Units	<b>20TBS2500</b>
Nominal Voltage per cell	Volts	2
Manufacturer's Name		Exide Industries Ltd.
Standards to which battery is manufactured		IS 1651
IS Nomenclature		
Number of cells in the battery bank		n
Nominal Voltage of Battery	Volts	2 X n
Declared Capacity at 27 degree C upto 1.80 ecv		
Initial	AH	2500
Rated	AH	2500
End of Life	AH	2000
Rated Capacity at minimum ambient temperature	Ah	As per formula: $C_t = C_{27}\{1 + 0.0043(t - 27)\}$
Rated Capacity at maximum ambient temperature	Ah	As per formula: $C_t = C_{27}\{1 + 0.0043(t - 27)\}$
Capacity in AH at various end cell voltages and duration of discharge		
	<b>E.C.V.</b>	<b>Ah output</b>
1 hour	1.67	1275.00
2 hour	1.70	1605.00
3 hour	1.75	1867.50
4 hour	1.76	1980.00
5 hour	1.77	2145.00
6 hour	1.77	2240.00
7 hour	1.78	2317.50
8 hour	1.78	2375.00
9 hour	1.80	2447.50
10 Hour	1.80	2500.00
Maximum momentary current for 1 min till 1.60 e.c.v		4500
Expected life of battery under normal operation & maintenance conditions	Years	15 years in stand-by float application
Internal Resistance of cell (IR)	milli ohms	0.12
Loss in capacity in 28 days due to self discharge	%	<8%
Recommended Charging rate for		
a) Float Charging		
i) Limit current	A	375
ii) Voltage	V	2.23 vpc
b) Boost charging		
i) Starting Current	A	300
ii) Finishing current	A	150
iii) Voltage	V	2.75
Trickle Charging Rate		
i) Minimum	mA	2500
ii) Maximum	mA	10000
Equalising charge		
a) Voltage	V	2.3
b) Current	A	125
c) Duration	Hrs.	6
d) Interval between successive equalising charge	Months	3
<b>Recommended Specific gravity at 27 deg C</b>		
a) for first filling		1.220 +/- 0.005
b) at full charge		1.240 +/- 0.005
c) when Battery is discharged at 10 hours rate		1.160 - 1.130

**Permissible max. temperature of Electrolyte**

i) During Initial Charging	deg C	50
ii) During Normal Operation	deg C	45

**Overall dimensions**

Each Cell L x W x H (tolerance of +/- 2 mm in each case)	mm	212 X 487 X 847
Complete Battery	mm	Depends on the battery layout
Distance between cell centres	mm	220
Quantity of Electrolyte per Cell	litres	49.3
Quantity of Electrolyte for battery (Including 10% extra)	litres	n X electrolyte per cell X 1.1

**Weight(+/-5%)**

Each cell		
without acid	kg	140.7
with acid	kg	200.8
Complete Battery without acid	kg	n X each cell weight without acid
with acid	kg	n X each cell weight with acid

**Material and type of Plates**

i) Positive Plates

Material		Lead-Antimony alloy spine
Height of Positive Plate	mm	570
Thickness of Positive Plate	mm	9.3
Area of Positive Plate	sqm	0.205
No. of positive plates per cell		20
Whether positive plates of individual cells are interchangeable		Yes, but not recommended

ii) Negative Plates

Material		Lead - Calcium alloy grid
Height of Negative Plate	mm	564
Thickness of Negative Plate	mm	4.5
Area of Negative Plate	sqm	0.2053
No. of negative plates per cell		20
Whether negative plates of individual cells are interchangeable		Yes, but not recommended

**Material and type of Separators**

Material		Synthetic fibre based material
Thickness of separator	mm	1.7
Clearance between bottom of the plate and the bottom of the container	mm	43
Clearance between top of the plates and top of container	mm	125.5
Whether explosion vents are offered		YES
Type of Vent and Filling Plugs		Explosion proof microporous ceramic made

### Container

Thickness of Container	mm	10
Material of Container		Transparent SAN

### Cover

Type of cover		Adhesive sealed
Material of Cover		Opaque SAN

### Connections

Material of Inter-Cell Connectors		Insulated Lead Plated Copper
Thickness of Inter-Cell Connectors	mm	5
Method of connection		Bolted
Inter-row, Inter-tier connectors and end take-offs furnished?		Yes
Material of Bolt, Nut and Washer for Inter-Cell and Cable Connections		Lead plated MS

### Racks

Racks		
a) Number of racks per battery		Depends on the battery layout
b) Number of cells per rack		Depends on the battery layout
c) Type of racks		Depends on the battery layout
d) Material of rack		Steel / Teak wood
e) Dimensions of the racks		Depends on the battery layout

### Ventilation requirements

Cubic content of battery rooms	m <sup>3</sup>	To be provided by customer
Gas generation per single cell per hour	Lit	80
No. of air exchanges required per hour		Depends on the size of battery room
Gasification Voltage per Cell	Volt	2.36
Recommended Max. period of cell storage before the first Charge (After Installation and filling of Electrolyte)		12 - 18 hours
Recommended Storage life of Battery (Dry shelf life)		12 months

## General Technical Particulars

Type of Cell	Units	<b>20TBS2600</b>
Nominal Voltage per cell	Volts	2
Manufacturer's Name		Exide Industries Ltd.
Standards to which battery is manufactured		IS 1651
IS Nomenclature		
Number of cells in the battery bank		n
Nominal Voltage of Battery	Volts	2 X n
Declared Capacity at 27 degree C upto 1.80 ecv		
Initial	AH	2600
Rated	AH	2600
End of Life	AH	2080
Rated Capacity at minimum ambient temperature	Ah	As per formula: $C_t = C_{27}\{1 + 0.0043(t - 27)\}$
Rated Capacity at maximum ambient temperature	Ah	As per formula: $C_t = C_{27}\{1 + 0.0043(t - 27)\}$
Capacity in AH at various end cell voltages and duration of discharge		
	<b>E.C.V.</b>	<b>Ah output</b>
1 hour	1.67	1326.00
2 hour	1.70	1669.20
3 hour	1.75	1942.20
4 hour	1.76	2059.20
5 hour	1.77	2230.80
6 hour	1.77	2329.60
7 hour	1.78	2410.20
8 hour	1.78	2470.00
9 hour	1.80	2545.40
10 Hour	1.80	2600.00
Maximum momentary current for 1 min till 1.60 e.c.v		4680
Expected life of battery under normal operation & maintenance conditions	Years	15 years in stand-by float application
Internal Resistance of cell (IR)	milli ohms	0.12
Loss in capacity in 28 days due to self discharge	%	<8%
Recommended Charging rate for		
a) Float Charging		
i) Limit current	A	390
ii) Voltage	V	2.23 vpc
b) Boost charging		
i) Starting Current	A	312
ii) Finishing current	A	156
iii) Voltage	V	2.75
Trickle Charging Rate		
i) Minimum	mA	2600
ii) Maximum	mA	10400
Equalising charge		
a) Voltage	V	2.3
b) Current	A	130
c) Duration	Hrs.	6
d) Interval between successive equalising charge	Months	3
<b>Recommended Specific gravity at 27 deg C</b>		
a) for first filling		1.220 +/- 0.005
b) at full charge		1.240 +/- 0.005
c) when Battery is discharged at 10 hours rate		1.160 - 1.130

**Permissible max. temperature of Electrolyte**

i) During Initial Charging	deg C	50
ii) During Normal Operation	deg C	45

**Overall dimensions**

Each Cell L x W x H (tolerance of +/- 2 mm in each case)	mm	212 X 487 X 847
Complete Battery	mm	Depends on the battery layout
Distance between cell centres	mm	220
Quantity of Electrolyte per Cell	litres	49
Quantity of Electrolyte for battery (Including 10% extra)	litres	n X electrolyte per cell X 1.1

**Weight(+/-5%)**

Each cell		
without acid	kg	145
with acid	kg	204.8
Complete Battery without acid	kg	n X each cell weight without acid
with acid	kg	n X each cell weight with acid

**Material and type of Plates**

i) Positive Plates

Material		Lead-Antimony alloy spine
Height of Positive Plate	mm	570
Thickness of Positive Plate	mm	9.3
Area of Positive Plate	sqm	0.205
No. of positive plates per cell		20
Whether positive plates of individual cells are interchangeable		Yes, but not recommended

ii) Negative Plates

Material		Lead - Calcium alloy grid
Height of Negative Plate	mm	564
Thickness of Negative Plate	mm	4.5
Area of Negative Plate	sqm	0.2053
No. of negative plates per cell		22
Whether negative plates of individual cells are interchangeable		Yes, but not recommended

**Material and type of Separators**

Material		Synthetic fibre based material
Thickness of separator	mm	1.7
Clearance between bottom of the plate and the bottom of the container	mm	43
Clearance between top of the plates and top of container	mm	125.5
Whether explosion vents are offered		YES
Type of Vent and Filling Plugs		Explosion proof microporous ceramic made

### Container

Thickness of Container	mm	10
Material of Container		Transparent SAN

### Cover

Type of cover		Adhesive sealed
Material of Cover		Opaque SAN

### Connections

Material of Inter-Cell Connectors		Insulated Lead Plated Copper
Thickness of Inter-Cell Connectors	mm	5
Method of connection		Bolted
Inter-row, Inter-tier connectors and end take-offs furnished?		Yes
Material of Bolt, Nut and Washer for Inter-Cell and Cable Connections		Lead plated MS

### Racks

Racks		
a) Number of racks per battery		Depends on the battery layout
b) Number of cells per rack		Depends on the battery layout
c) Type of racks		Depends on the battery layout
d) Material of rack		Steel / Teak wood
e) Dimensions of the racks		Depends on the battery layout

### Ventilation requirements

Cubic content of battery rooms	m <sup>3</sup>	To be provided by customer
Gas generation per single cell per hour	Lit	83.2
No. of air exchanges required per hour		Depends on the size of battery room
Gasification Voltage per Cell	Volt	2.36
Recommended Max. period of cell storage before the first Charge (After Installation and filling of Electrolyte)		12 - 18 hours
Recommended Storage life of Battery (Dry shelf life)		12 months

## General Technical Particulars

Type of Cell	Units	<b>22TBS2900</b>
Nominal Voltage per cell	Volts	2
Manufacturer's Name		Exide Industries Ltd.
Standards to which battery is manufactured		IS 1651
IS Nomenclature		
Number of cells in the battery bank		n
Nominal Voltage of Battery	Volts	2 X n
Declared Capacity at 27 degree C upto 1.80 ecv		
Initial	AH	2900
Rated	AH	2900
End of Life	AH	2320
Rated Capacity at minimum ambient temperature	Ah	As per formula: $C_t = C_{27}\{1 + 0.0043(t-27)\}$
Rated Capacity at maximum ambient temperature	Ah	As per formula: $C_t = C_{27}\{1 + 0.0043(t-27)\}$
Capacity in AH at various end cell voltages and duration of discharge		
	<b>E.C.V.</b>	<b>Ah output</b>
1 hour	1.67	1479.00
2 hour	1.70	1861.80
3 hour	1.75	2166.30
4 hour	1.76	2296.80
5 hour	1.77	2488.20
6 hour	1.77	2598.40
7 hour	1.78	2688.30
8 hour	1.78	2755.00
9 hour	1.80	2839.10
10 Hour	1.80	2900.00
Maximum momentary current for 1 min till 1.60 e.c.v		5220
Expected life of battery under normal operation & maintenance conditions	Years	15 years in stand-by float application
Internal Resistance of cell (IR)	milli ohms	0.11
Loss in capacity in 28 days due to self discharge	%	<8%
Recommended Charging rate for		
a) Float Charging		
i) Limit current	A	435
ii) Voltage	V	2.23 vpc
b) Boost charging		
i) Starting Current	A	348
ii) Finishing current	A	174
iii) Voltage	V	2.75
Trickle Charging Rate		
i) Minimum	mA	2900
ii) Maximum	mA	11600
Equalising charge		
a) Voltage	V	2.3
b) Current	A	145
c) Duration	Hrs.	6
d) Interval between successive equalising charge	Months	3
<b>Recommended Specific gravity at 27 deg C</b>		
a) for first filling		1.220 +/- 0.005
b) at full charge		1.240 +/- 0.005
c) when Battery is discharged at 10 hours rate		1.160 - 1.130



**Permissible max. temperature of Electrolyte**

i) During Initial Charging	deg C	50
ii) During Normal Operation	deg C	45

**Overall dimensions**

Each Cell L x W x H (tolerance of +/- 2 mm in each case)	mm	212 X 576 X 847
Complete Battery	mm	Depends on the battery layout
Distance between cell centres	mm	220
Quantity of Electrolyte per Cell	litres	60.1
Quantity of Electrolyte for battery (Including 10% extra)	litres	n X electrolyte per cell X 1.1

**Weight(+/-5%)**

Each cell		
without acid	kg	158.5
with acid	kg	231.8
Complete Battery without acid	kg	n X each cell weight without acid
with acid	kg	n X each cell weight with acid

**Material and type of Plates**

i) Positive Plates

Material		Lead-Antimony alloy spine
Height of Positive Plate	mm	570
Thickness of Positive Plate	mm	9.3
Area of Positive Plate	sqm	0.205
No. of positive plates per cell		22
Whether positive plates of individual cells are interchangeable		Yes, but not recommended

ii) Negative Plates

Material		Lead - Calcium alloy grid
Height of Negative Plate	mm	564
Thickness of Negative Plate	mm	4.5
Area of Negative Plate	sqm	0.2053
No. of negative plates per cell		24
Whether negative plates of individual cells are interchangeable		Yes, but not recommended

**Material and type of Separators**

Material		Synthetic fibre based material
Thickness of separator	mm	1.7
Clearance between bottom of the plate and the bottom of the container	mm	43
Clearance between top of the plates and top of container	mm	125.5
Whether explosion vents are offered		YES
Type of Vent and Filling Plugs		Explosion proof microporous ceramic made

### Container

Thickness of Container	mm	10
Material of Container		Transparent SAN

### Cover

Type of cover		Adhesive sealed
Material of Cover		Opaque SAN

### Connections

Material of Inter-Cell Connectors		Insulated Lead Plated Copper
Thickness of Inter-Cell Connectors	mm	5
Method of connection		Bolted
Inter-row, Inter-tier connectors and end take-offs furnished?		Yes
Material of Bolt, Nut and Washer for Inter-Cell and Cable Connections		Lead plated MS

### Racks

Racks		
a) Number of racks per battery		Depends on the battery layout
b) Number of cells per rack		Depends on the battery layout
c) Type of racks		Depends on the battery layout
d) Material of rack		Steel / Teak wood
e) Dimensions of the racks		Depends on the battery layout

### Ventilation requirements

Cubic content of battery rooms	m <sup>3</sup>	To be provided by customer
Gas generation per single cell per hour	Lit	92.8
No. of air exchanges required per hour		Depends on the size of battery room
Gasification Voltage per Cell	Volt	2.36
Recommended Max. period of cell storage before the first Charge (After Installation and filling of Electrolyte)		12 - 18 hours
Recommended Storage life of Battery (Dry shelf life)		12 months

## General Technical Particulars

Type of Cell	Units	<b>24TBS3000</b>
Nominal Voltage per cell	Volts	2
Manufacturer's Name		Exide Industries Ltd.
Standards to which battery is manufactured		IS 1651
IS Nomenclature		
Number of cells in the battery bank		n
Nominal Voltage of Battery	Volts	2 X n
Declared Capacity at 27 degree C upto 1.80 ecv		
Initial	AH	3000
Rated	AH	3000
End of Life	AH	2400
Rated Capacity at minimum ambient temperature	Ah	As per formula: $C_t = C_{27}\{1 + 0.0043(t - 27)\}$
Rated Capacity at maximum ambient temperature	Ah	As per formula: $C_t = C_{27}\{1 + 0.0043(t - 27)\}$
Capacity in AH at various end cell voltages and duration of discharge		
	<b>E.C.V.</b>	<b>Ah output</b>
1 hour	1.67	1530.00
2 hour	1.70	1926.00
3 hour	1.75	2241.00
4 hour	1.76	2376.00
5 hour	1.77	2574.00
6 hour	1.77	2688.00
7 hour	1.78	2781.00
8 hour	1.78	2850.00
9 hour	1.80	2937.00
10 Hour	1.80	3000.00
Maximum momentary current for 1 min till 1.60 e.c.v		5400
Expected life of battery under normal operation & maintenance conditions	Years	15 years in stand-by float application
Internal Resistance of cell (IR)	milli ohms	0.1
Loss in capacity in 28 days due to self discharge	%	<8%
Recommended Charging rate for		
a) Float Charging		
i) Limit current	A	450
ii) Voltage	V	2.23 vpc
b) Boost charging		
i) Starting Current	A	360
ii) Finishing current	A	180
iii) Voltage	V	2.75
Trickle Charging Rate		
i) Minimum	mA	3000
ii) Maximum	mA	12000
Equalising charge		
a) Voltage	V	2.3
b) Current	A	150
c) Duration	Hrs.	6
d) Interval between successive equalising charge	Months	3
<b>Recommended Specific gravity at 27 deg C</b>		
a) for first filling		1.220 +/- 0.005
b) at full charge		1.240 +/- 0.005
c) when Battery is discharged at 10 hours rate		1.160 - 1.130

**Permissible max. temperature of Electrolyte**

i) During Initial Charging	deg C	50
ii) During Normal Operation	deg C	45

**Overall dimensions**

Each Cell L x W x H (tolerance of +/- 2 mm in each case)	mm	212 X 576 X 847
Complete Battery	mm	Depends on the battery layout
Distance between cell centres	mm	220
Quantity of Electrolyte per Cell	litres	58.7
Quantity of Electrolyte for battery (Including 10% extra)	litres	n X electrolyte per cell X 1.1

**Weight(+/-5%)**

Each cell		
without acid	kg	164.9
with acid	kg	236.5
Complete Battery without acid	kg	n X each cell weight without acid
with acid	kg	n X each cell weight with acid

**Material and type of Plates**

i) Positive Plates

Material		Lead-Antimony alloy spine
Height of Positive Plate	mm	570
Thickness of Positive Plate	mm	9.3
Area of Positive Plate	sqm	0.205
No. of positive plates per cell		24
Whether positive plates of individual cells are interchangeable		Yes, but not recommended

ii) Negative Plates

Material		Lead - Calcium alloy grid
Height of Negative Plate	mm	564
Thickness of Negative Plate	mm	4.5
Area of Negative Plate	sqm	0.2053
No. of negative plates per cell		24
Whether negative plates of individual cells are interchangeable		Yes, but not recommended

**Material and type of Separators**

Material		Synthetic fibre based material
Thickness of separator	mm	1.7
Clearance between bottom of the plate and the bottom of the container	mm	43
Clearance between top of the plates and top of container	mm	125.5
Whether explosion vents are offered		YES
Type of Vent and Filling Plugs		Explosion proof microporous ceramic made

### Container

Thickness of Container	mm	10
Material of Container		Transparent SAN

### Cover

Type of cover		Adhesive sealed
Material of Cover		Opaque SAN

### Connections

Material of Inter-Cell Connectors		Insulated Lead Plated Copper
Thickness of Inter-Cell Connectors	mm	5
Method of connection		Bolted
Inter-row, Inter-tier connectors and end take-offs furnished?		Yes
Material of Bolt, Nut and Washer for Inter-Cell and Cable Connections		Lead plated MS

### Racks

Racks		
a) Number of racks per battery		Depends on the battery layout
b) Number of cells per rack		Depends on the battery layout
c) Type of racks		Depends on the battery layout
d) Material of rack		Steel / Teak wood
e) Dimensions of the racks		Depends on the battery layout

### Ventilation requirements

Cubic content of battery rooms	m <sup>3</sup>	To be provided by customer
Gas generation per single cell per hour	Lit	96
No. of air exchanges required per hour		Depends on the size of battery room
Gasification Voltage per Cell	Volt	2.36
Recommended Max. period of cell storage before the first Charge (After Installation and filling of Electrolyte)		12 - 18 hours
Recommended Storage life of Battery (Dry shelf life)		12 months

## General Technical Particulars

Type of Cell	Units	<b>24TBS3200</b>
Nominal Voltage per cell	Volts	2
Manufacturer's Name		Exide Industries Ltd.
Standards to which battery is manufactured		IS 1651
IS Nomenclature		
Number of cells in the battery bank		n
Nominal Voltage of Battery	Volts	2 X n
Declared Capacity at 27 degree C upto 1.80 ecv		
Initial	AH	3200
Rated	AH	3200
End of Life	AH	2560
Rated Capacity at minimum ambient temperature	Ah	As per formula: $C_t = C_{27}\{1 + 0.0043(t - 27)\}$
Rated Capacity at maximum ambient temperature	Ah	As per formula: $C_t = C_{27}\{1 + 0.0043(t - 27)\}$
Capacity in AH at various end cell voltages and duration of discharge		
	<b>E.C.V.</b>	<b>Ah output</b>
1 hour	1.67	1632.00
2 hour	1.70	2054.40
3 hour	1.75	2390.40
4 hour	1.76	2534.40
5 hour	1.77	2745.60
6 hour	1.77	2867.20
7 hour	1.78	2966.40
8 hour	1.78	3040.00
9 hour	1.80	3132.80
10 Hour	1.80	3200.00
Maximum momentary current for 1 min till 1.60 e.c.v		5760
Expected life of battery under normal operation & maintenance conditions	Years	15 years in stand-by float application
Internal Resistance of cell (IR)	milli ohms	0.1
Loss in capacity in 28 days due to self discharge	%	<8%
Recommended Charging rate for		
a) Float Charging		
i) Limit current	A	480
ii) Voltage	V	2.23 vpc
b) Boost charging		
i) Starting Current	A	384
ii) Finishing current	A	192
iii) Voltage	V	2.75
Trickle Charging Rate		
i) Minimum	mA	3200
ii) Maximum	mA	12800
Equalising charge		
a) Voltage	V	2.3
b) Current	A	160
c) Duration	Hrs.	6
d) Interval between successive equalising charge	Months	3
<b>Recommended Specific gravity at 27 deg C</b>		
a) for first filling		1.220 +/- 0.005
b) at full charge		1.240 +/- 0.005
c) when Battery is discharged at 10 hours rate		1.160 - 1.130

**Permissible max. temperature of Electrolyte**

i) During Initial Charging	deg C	50
ii) During Normal Operation	deg C	45

**Overall dimensions**

Each Cell L x W x H (tolerance of +/- 2 mm in each case)	mm	212 X 576 X 847
Complete Battery	mm	Depends on the battery layout
Distance between cell centres	mm	220
Quantity of Electrolyte per Cell	litres	58.4
Quantity of Electrolyte for battery (Including 10% extra)	litres	n X electrolyte per cell X 1.1

**Weight(+/-5%)**

Each cell		
without acid	kg	170
with acid	kg	241.2
Complete Battery without acid	kg	n X each cell weight without acid
with acid	kg	n X each cell weight with acid

**Material and type of Plates**

i) Positive Plates

Material		Lead-Antimony alloy spine
Height of Positive Plate	mm	570
Thickness of Positive Plate	mm	9.3
Area of Positive Plate	sqm	0.205
No. of positive plates per cell		24
Whether positive plates of individual cells are interchangeable		Yes, but not recommended

ii) Negative Plates

Material		Lead - Calcium alloy grid
Height of Negative Plate	mm	564
Thickness of Negative Plate	mm	4.5
Area of Negative Plate	sqm	0.2053
No. of negative plates per cell		26
Whether negative plates of individual cells are interchangeable		Yes, but not recommended

**Material and type of Separators**

Material		Synthetic fibre based material
Thickness of separator	mm	1.7
Clearance between bottom of the plate and the bottom of the container	mm	43
Clearance between top of the plates and top of container	mm	125.5
Whether explosion vents are offered		YES
Type of Vent and Filling Plugs		Explosion proof microporous ceramic made

### Container

Thickness of Container	mm	10
Material of Container		Transparent SAN

### Cover

Type of cover		Adhesive sealed
Material of Cover		Opaque SAN

### Connections

Material of Inter-Cell Connectors		Insulated Lead Plated Copper
Thickness of Inter-Cell Connectors	mm	5
Method of connection		Bolted
Inter-row, Inter-tier connectors and end take-offs furnished?		Yes
Material of Bolt, Nut and Washer for Inter-Cell and Cable Connections		Lead plated MS

### Racks

Racks		
a) Number of racks per battery		Depends on the battery layout
b) Number of cells per rack		Depends on the battery layout
c) Type of racks		Depends on the battery layout
d) Material of rack		Steel / Teak wood
e) Dimensions of the racks		Depends on the battery layout

### Ventilation requirements

Cubic content of battery rooms	m <sup>3</sup>	To be provided by customer
Gas generation per single cell per hour	Lit	102.4
No. of air exchanges required per hour		Depends on the size of battery room
Gasification Voltage per Cell	Volt	2.36
Recommended Max. period of cell storage before the first Charge (After Installation and filling of Electrolyte)		12 - 18 hours
Recommended Storage life of Battery (Dry shelf life)		12 months